

Price RUBBER CORP.

2733 Gunter Park Dr. W. • Montgomery, AL 36109
(334) 277-5470 • (888) 778-7707 • Fax: (334) 279-5603

Email: sales@pricerubber.com

Material / Compound Characteristics

22 PRC GRD II / #760 TOPFLITE

“SNOW PLOW RUBBER”

*Compound Physical Properties—Textured Impression Finish

ASTM D 412 —

TENSILE	—	2400 psi (15.9 MPa) minimum
Modulus @ 100%	—	500 psi (typical)
Modulus @ 200%	—	900 psi (typical)
Modulus @ 300%	—	1200 psi (typical)
Elongation @ Break	—	450 % minimum

ASTM D2240: Hardness — 60 ± 5 Durometer (Shore A)

ASTM D 624: Tear Resistance (Die C) — 229 ppi (lbs per inch) minimum

ASTM D 297: Density / Specific Gravity— 1.135 typical

ASTM D 395: Compression Set:

22 hrs. @ 158° F	—	15% typical (25% max)
22 hrs. @ 212° F	—	25% typical (50% max.)

ASTM D 573: Deterioration of Properties (% Difference from Originals) (Heat Aging – Air Oven)

70 hrs. 158° F	Tensile	—	-20% max.
	Elongation	—	-35% max.
	Durometer	—	± 6 pts. max

ASTM D 2137: Low Temperature Brittleness (- 40° F) — Pass

ASTM D 2137: Ozone Resistance (3 days @ 25 pphm) — Pass